



## ***PAXOLIN SHEETS (SRBP)***

*Paxolin (SRBP) is a phenolic paper laminate offering good mechanical and electrical properties in low voltage applications. The material offers excellent machining characteristics and punching quality up to 2.5mm*

### MATERIAL CHARACTERISTICS

Density	approx. 1.4g.cm <sup>3</sup>
Flexural strength	150 MPa
Flexural modulus of elasticity	approx. 9000 MPa
Tensile strength	120 MPa
Electrical strength at 90C in oil perpendicular to laminations (3mm thick)	5 kV/mm
Breakdown voltage at 90°C in oil parallel to laminations	300 MPa
Permittivity at 50Hz and 1Hz	< 5.5
Comparative tracking index	CTI 100
Impact strength a <sub>n</sub> 10 & a <sub>n</sub> 15	20 KJ/m <sup>2</sup>
RoHS compliant	yes

Part no.	Sheet size	Thickness
E50030	4 x 4 feet	3mm (1/8")
E50060	4 x 4 feet	6mm (1/4")
E50090	4 x 4 feet	9mm (3/8")



## ***ELECTRICAL SWITCHGEAR MATTING***

*Electrical Switchgear matting is electrically tested and is available in two thicknesses and in a fluted form. Suitable for insulation purposes this matting is sold in 11.5m rolls or by the linear meter.*

### MATERIAL CHARACTERISTICS

Operating voltage	6mm thickness 11Kv, working 450V 9.5mm thickness 15Kv, working 650V
Grade	No 8
Hardness shore A	65
Specific gravity	1.5
Tensile strength	8 MPa
Abrasion resistance	200mm <sup>3</sup>
Tear resistance	20 kg/cm
RoHS compliant	yes

Part no.	Supplied thickness mm	Width mm	Roll size m
G70609	6.0	915	11.5
G70909	9.5	915	11.5

Birch Valley Plastics Ltd, Darklake View, Estover, Plymouth PL6 7TL, England  
 Telephone: +44 (0)1 752 696515 Fax: +44 (0)1 752 696724

1 Enterprise Close, Factory Lane, Croydon CR0 3RZ, England  
 Telephone: +44 (0)20 8665 8100 Fax: +44 (0)208 8665 8101